



Technical Data Sheet

WG -201 IPA-Based Conductive Ink

SG-201 is an electrically conductive ink/coating formulated with Graphene Nanoplatelets for application by gravure or flexographic printing. This product has an excellent adhesion to a variety of substrates. SG-201 provides an alternative to meet your printing needs without sacrificing performance..

IPA Based Ink WG-201 Typical Properties	
Sheet resistivity (Ω /sq/mil)	<20
Density (lb/gal)	7.6
Drying (minutes @ 70 degrees Celcius)	5-10 minutes
Viscosity (cps)	100-125
Solids (%)	18
Thinner	IPA

Note: The table shows anticipated typical properties for WG-201 based on specific controlled experiments in our labs and are not intended to represent the product specifications, detail of which are available upon request.

Mixing and Dilution

Thoroughly mix SG-201 with an agitator or a paint shaker before use. If necessary, add thinner while mixing..

Drying

Coated parts should be dried at 70°C for 5-10 minutes immediately after printing.

Clean up Solvent

IPA

Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).

Storage and Shelf Life

Container should be stored, tightly sealed in a clean and stable environment at room temperature. Avoid high heat or freezing. Shelf life of material in unopened containers is six months from the date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Cometox s.r.l. believes the information in this technical data sheet to be accurate at publication. Cometox s.r.l. does not assume any obligation or liability for the information in this technical data sheet. No warranties are given. All implied warranties of fitness for a particular purpose are expressly excluded. No freedom from infringement of any patent owned by Cometox s.r.l. or other is to be inferred. Cometox s.r.l. encourages its customers to review their manufacturing processes and applications for Graphene Nanoplatelets from the standpoint of human health and environmental quality to ensure that this material is not utilized in ways that it is not intended or tested. Product literature and safety data sheets should be consulted prior to use.

Cometox s.r.l.

Via XX settembre, 9

20080 Zibido San Giacomo MI Italy

Phone : +39 02 90003777 – Fax : +39 02 90003787 - Mail : info@cometox.it

